Translucent



Affiliated to Yunsion Industrial Materials Pvt. Ltd.

9307TL (RTV Silicone)

PRODUCT DESCRIPTIONS

One-Component (Room Temperature Vulcanizing) silicone sealant;

TECHNICAL DATA SHEET

- It has good flow performance, and has good extrusion performance In the range of $4 \sim 40^{\circ}$ C;
- No corrosion to metal, glass, gypsum board, marble and plastic etc, and good adhesion performance
- Excellent weather resistance, good waterproof and insulation properties;
- High temperature and low temperature resistance, and at - 40°C of low temperature will not become brittle, hardening or cracking, at the temperature of 180°C will not soften, degradation after cured, and always maintain good elasticity.
- Comply with EU ROHS directive requirements.

PRODUCT APPLICATION

- Insulation seal for electrical switch
- Insulation seal for relays and other electronic components
- LED lamp adhesive, waterproof, insulation, sealing

PRODUCT INSTRUCTION

- Please make sure the coated surface is absolutely clean and dry, and remove the rust, dust and oil stains on the surface before use.
- Cut the projecting part on the top of the tube, then squeeze out the glue on the objects and apply it evenly
- If the thickness of glue applied on the objects ranges from 2mm to 4mm, it's better to place the objects under indoor temperature and with 55% relative humidity, then it'll cure naturally within 24 hours. But if the thickness of glue applied on the objects surpasses 6mm. it'll takes at least 7 days to cure under the same condition.
- Please store the glue sealed after used;

CAUTION

This product is non-toxic after completely cured, but should avoid contact with the eyes and children before curing, and working area maintain ventilation

TECHNICAL SPECIFICATIONS

Performance	Data
Colour	Translucent
Mobility	No flow
Surface dry time (min)	3-6
Full cure time (H)	24
Tensile strength (Mpa)	0.45
Viscosity (mPa.s)	300000
Density (g/ml)	1.05 ± 0.08
Hardness (ShoreA)	28
Volume resistivity (Ω·CM)	3.5*×10 ¹⁴

PACKAGING SPECIFICATIONS

50ML/Tube	(200 Tubes per carton box)
300ML/Tube	(25 Tubes per carton box)
2600ML/Tube	(4 Tubes per carton Box)

STORAGE AND TRANSPORT

- This product should be stored in a dry, cool place, avoid rain, sun exposure, storage period of five months (25°C).
- Such products are non hazardous and can be transported in general chemicals





